

**PASTE "TI-ZERO"****TECHNICAL SPECIFICATION**

Characteristics	Reference	Test method
Bentonite content, %	Min 88	BSS EN 965
Content montmorillonite, %	Min 85	
Swell index, ml/2g	Min 22	ASTM D 5890
Fluid loss, ml	Max 18	ASTM D 5891